


KLINGERSIL® C-4300

Universal high-pressure gasket material

KLINGERSIL® C-4300 is a universal high-pressure gasket material that is resistant to hot water, steam, oil, hydrocarbons and many other chemicals which makes it suitable for many different media.

This compressed fiber gasket material is manufactured with aramid fiber reinforced with a nitrile binder.



TYPICAL VALUES REFER TO 1/16" THICK MATERIAL UNLESS NOTED


Creep relaxation ASTM F38B (1/32")	25 %
Sealability ASTM F37A (1/32")	< 0.25 ml/hr
Gas Permeability DIN 3535/6	< 0.5 ml/min
Compressibility ASTM F36J	7 - 17 %
Recovery ASTM F36J	50 % minimum
KLINGER Hot Compression Test	
Thickness Decrease 73°F (23°C)	15 % initial
Thickness Decrease 572°F (300°C)	25 % additional
Weight Increase ASTM F146 after immersion in Fuel B, 5h/73°F (23°C)	10 % maximum
Thickness Increase ASTM F146 after immersion in	
ASTM Oil IRM 901, 5h/300°F (149°C)	0 - 5 %
ASTM Oil IRM 903, 5h/300°F (149°C)	0 - 5 %
ASTM Fuel A, 5h/73°F (23°C)	0 - 5 %
ASTM Fuel B, 5h/73°F (23°C)	0 - 10 %
Dielectric Strength ASTM D149-95a	18 kV/mm
Density ASTM F1315	100 lb/ft ³ (1.6 g/cc ³)
Leachable Chloride Content FSA Method	200 ppm
ASTM F104 Line Call Out	F712111B4E12K6M4
Color	Black or white

KLINGERSIL® C-4300


The pressure/temperature graphs shown are the most current method of determining the suitability of a gasket material in a known environment. However, chemical compatibility must also be considered.

pT diagram for thickness 1/16”:

LIQUIDS



GASES & STEAM



In area ① the gasket material is suitable using common installation practices subject to chemical compatibility.

In area ② appropriate measures are necessary for installation of the gasket to ensure maximum performance. Please call or refer to KLINGERexpert for assistance.

In area ③ do not install gaskets in these applications without first referring to KLINGERexpert or contacting KLINGER’s technical support service.

The ability of a gasket to make and maintain a seal depends not only on the style and quality of the gasket material, but also on medium being sealed, the flange design, the amount of pressure applied to the gasket by the bolts and how the gasket is assembled onto the flanges and tightened. These factors are beyond the manufacturer’s control.

KLINGER Thermoseal

2350 Campbell Road, Sidney, Ohio 45365

Tel: +1 937 498 2222